

Application No. 10/590,932
Reply to Office Action of September 3, 2009

IN THE SPECIFICATION

Please amend the table at page 32 as shown on the following page.

Application No. 10/590,932
Reply to Office Action of September 3, 2009

Ex.	Fractions [% by weight]					Elongation at break without thermal stress [%]	Elongation at break after 10 days at 60°C [%]	Ratio of after/without thermal stress [%]
	PMMA [%]	PVDF [%]	Film thickness [μm]	Elastomer particle content of the PMMA fraction [%]				
A	30	70	500	65		262	177	68
A-Comp.	30	70	500	0		293	14	5
B	30	70	250	65		299	292	98
B-Comp.	30	70	250	0		442	7	2
C-Comp.	30	70	50	65		355	305	86
D-Comp.	30	70	50	0		393	321	82
E	40	60	200	60		273	205	75
F	40	60	200	40		357	292	82
G-Comp.	40	60	200	20		331	9	3

Comp. = comparative example
“PMMA” means standard PMMA or impact-modified PMMA